

Stone Sealer

Technical Data Sheet and Instructions for Use

Characteristics

Clear long-term protection for outdoor use.



- hinders growth of algae, moss and lichen
- water repellent
- oil and dirt repellent
- lightfast and weather-resistant
- breathable
- filmforming – strengthens the substrate
- non-slip
- alkali-resistant

Recommended Use

For all **absorbent** natural and artificial stones such as terracotta, lime sand brick, slate, marble, open-pore clinker brick, exposed concrete and concrete artificial stone. Thanks to its high durability it is also suitable for alkaline substrates such as concrete and plaster.

For floors, stairs, patios, window sills and also for the maintenance of memorial and gravestones.

Processing/Application

| | | |
|--------------------------------|---|--|
| Coating methods: |  Brush |  Roller |
| Yield (m ² /Litre): | 5–10 | 5–10 |

according to the absorbency of the substrate

Technical data

| | |
|-------------------------------|------------------|
| Thinning: | none |
| Working viscosity: | ready for use |
| Viscosity: | 23 sec / 4mm DIN |
| Density (g/cm ³): | 0.789 |

Drying

(at 20°C and 50% relative humidity)

| | |
|------------|------------------|
| Recoating: | after 30 minutes |
| Walk over: | after 2–3 hours |

Cleaning

Clean tools immediately after use with CLOU® EV-Thinner.

Storage/disposal

Store in well-sealed original containers in a cool place protected from frost. Stone Sealer reacts with humidity. Leftover product must under special treatment in compliance with the official regulations. The final determination must be coordinated through the regional waste utility.

Safety instructions

Do not drain into the ground water or sewage system.

Processing instructions

Preparation: Ensure that the surface to be sealed is clean, dry and free of any oil or grease. Remove all traces of algae, moss and lichen.

Apply one to two coats of Stone Sealer evenly with a brush or roller. The second coat must be applied as soon as the first coat has dried, in order to ensure good bonding between the coats.

It is possible to coat by dipping or spraying without any problems.

The Sealer is already dry after a short time but should be protected from the effects of moisture for two days.

Ordering

Container sizes: 0.75 / 2.5 Litre

Item code:

| | |
|--------------|-------------|
| Stone Sealer | 18882.00000 |
| EV Thinner | 35070.00000 |

This information can only be of a non-binding nature.
The processing and directions for use may have to be adapted to prevailing working conditions.

CLOU®